



0-0-21.5

Chemical Composition					
Component	Symbol	Typical	Guarantee		
Potassium Oxide Equivalent	K <sub>2</sub> O	21.7 %	21.5% Minimum		
Magnesium	Mg	11.3 %	10.5% Minimum		
Sulfur	S	21.7 %	21% Minimum		
Chloride	Cl-	2.0 %	2.5% Maximum		
Moisture	$H_2O$	0.1 %			

Particle Size Di	stribution Cumu	ulative %		
Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
4	4	4.75	0 - 2	0
5	5	4.00	0 - 15	7
6	6	3.35	10 - 45	21
7	7	2.80	25 - 75	48
8	8	2.36	70 - 98	80
9	10	2.00	90 - 100	96
10	12	1.70	95 - 100	99.5
12	14	1.40	98 - 100	99.9
14	16	1.18	99 - 100	99.9

Physical Properties	
Parameter	Typical
Bulk Density (Loose)	
- lb/ft³	82
- kg/m³	1307
Angle of Repose	29 Degrees

Sizing Characteristics	
Parameter	Typical
Size Guide Number (SGN)	280
Uniformity Index (UI)	52

## Please refer to the Safety Data Sheet (SDS #: MOS100042) for additional information (www.mosaicco.com)

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values Additional handling, transportation, or improper/extended storage may affect product analyses. Mosaic disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.